

BENFER GRIP



**Special adhesive
highly resistant,
thixotropic,
high strength
and long open time**

- Overlapping internal old floors
- Extra white
- High resistance to sliding
- Application without the need of spacers
- Perfect for glass and ceramic mosaics
- Perfect for Klinker and thick floor coverings
- Its smooth consistency reduces fatigue
- Long open time
- Mixed with CEMLATEX 600 conforms to EN12004 C2 TE S2
- *FLEXIBLE, deformability > 2 mm*

EN 12004
C2TE



Via Paletti snc - Castelnovo Rangone (Mo), 41051 - Italy - tel. +39 059 535 540 - fax +39 059 538 338
P.IVA IT00611061201 - C.F. e Iscr. Reg. Impr. di Modena 03304180379 - R.E.A. MO-385501 - Cap. Soc. €500.000,00 i.v.

info@benfer.it - www.benfer.it





Hi-tech adhesive, extra-white, with no vertical sliding, frost-proof. Perfect for laying mosaic (glass, marble, porcelain), porcelain tiles and single-fired wall and floor tiles. Laying of thick floor coverings. High final resistances and extended open time.

Fields of application:

Laying of porcelain, single fired and non-absorbent tiles, glass and ceramic mosaic, stable natural stones:

- for Interior and exterior walls and floors
- suitable for heavy duty areas (with CEMLATEX 600)
- private and public swimming pools (with CEMLATEX 600)

Product Technical Data

Basis:	cement, aggregates, additives
Colour:	Extra white and grey
Apparent mass volume:	1,25 kg/dm ³
Maximum grain size:	0,5 mm
Storage and Duration :	12 months in the original closed package in a cool dry place
Danger of toxicity:	No. The product may cause irritation to the eyes and skin due to presence of cement
Inflammable:	No
Mixture ratio:	31 %, 7,75 lt water/25 kg bag
Mixture consistency:	creamy
Density of paste:	1,60 kg/dm ³
Application temperature:	From + 5°C to + 35°C
Pot life:	about 3 hours*
Open time:	30 minutes*
Vertical sliding to EN 1308:	< 0,5 mm
Maximum thickness:	15 mm
Foot tyraffic after :	12 hours*
Grouting:	12 hours*
Full service:	7 days*
Final hardening:	28 days*
Deformability according EN 12004:	2,0 mm
Temperature resistance:	from -30° C to +90° C, *at 23°C and 50% relative humidity

For more information see the valid technical data sheet and safety sheets of the product and watch the video application on www.benfer.it



Via Paletti snc - Castelnuovo Rangone (Mo), 41051 - Italy - tel. +39 059 535 540 - fax +39 059 538 338
P.IVA IT00611061201 - C.F. e Iscr. Reg. Impr. di Modena 03304180379 - R.E.A. MO-385501 - Cap. Soc. €500.000,00 i.v.

info@benfer.it - www.benfer.it

